

PRIMER 900

Technical and Environmental Data Sheet

NAME:	PRIMER 900
TYPE:	water-based primer
USE:	grey water-based primer for indoor easy to apply.
COMPOSITION:	special resins and charges allowing breath-
CHARACTERISTICS:	specific weight: 1.490 ± 30 gr/LT. at 20°C
	yield: 10 - 11 m ² /LT. for a coating (it may vary according to the roughness, surface absorption and application methods)
	colours: grey
	packaging: LT. 0,500 - LT. 1
DRYING:	on the surface: 2 hours at 20°C
	overpainting : 4 - 6 hours at 20°C
	in depth: 24 hours at 20°C

CHARACTERISTICS AND RESISTANCE: grey water-based primer necessary to get the decorative effects of Klondike both indoor and outdoor. Primer 900 is easy to apply and it is characterised by a good covering, resistance and washability. It can be applied on several surfaces as cement, plaster, plaster of Paris, plasterboard, wood and iron and even on surfaces that have already been already painted (provided that the existing coat is not peeling).

ENVIROMENTAL PERFORMANCES

PERFORMANCES	STANDAR D RULE	VALUE	BRAND
ABSENCE OF DANGEROUS SUBSTANCES	-	FREE	
FORMALDEHYDE ISSUE RATE , X	JIS A 1902-3	X < 0.005 mg/m ² h F****	
VOC On product to use	Directive 2004-42-CE	max 15 g/L (Ue Limit 200 g/L) A/1 Cat.	

PREPARATION OF THE PRODUCTS: APPLICATION:

dilution: ready to use

system: by brush-by roller-by spray
number of coatings: 1 - 2 or more to cover

PREPARATION OF THE SURFACE:

Old walls. Remove old non-adhering and peeling paint and wash using water and a suitable soap product. Next, apply a fixative suited to the type of surface. When the fixative is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE. **New walls.** Clean (and if necessary, fill) the surface you wish to paint. Once it is dry, sand the surface and apply a coat of suitable fixative. When the fixative is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE. **Wood, glass, light alloys and painted iron.** Remove all grease from the surface and sand well, so that it is smooth and clean.

SC 00219

Apply a coat of primer which is suited to that particular type of surface, then apply a coat of PRIMER 900. After 6 hours at 20°C, proceed with the application of KLONDIKE. **New iron (not treated)**. Remove all grease and any layers of rust from the surface and apply one coat (or more) of a suitable anti-rust treatment. When this is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE.

Application temperature: above + 5 ° C and below + 30 ° C.

Storage: in a tightly closed tin, even after use, at temperatures above + 5 ° C and below + 30 ° C.

Stability: approximately 2 years in well-sealed and never opened packages.

NOTES:

Mix well before use ,Wash the tools with water, immediately after using,with water and soap.

**Technical Sheet n° SC 00219 issued by the Responsible Quality Control:
Edition n° 3 December 2019**